

TECHNICAL DATA SHEET

PRODUCT IDENTIFICATION : OTOKAP PRINT

TECHNICAL PROPERTIES

DESCRIPTION	STANDARD	UNIT	PRODUCT							
Back Layer			TX100	TX150	TX150	TX150	TX150	TX150	TX150	TX150
Total Thickness	EN ISO 24346	mm	1.20	1.40	1.60	1.80	2	2.2	2	2.2
Wear Layer Thickness	EN ISO 24340	mm	0.15	0.15	0.15	0.15	0.15	0.15	0.30	0.30
Unit Area Mass	EN ISO 23997	g/m ²	1210	1450	1810	2055	2475	2690	2350	2680
Roll Width	EN ISO 24341	m	2	2	2	2	2	2	2	2
Roll Length	EN ISO 24341	m	18-20	18-20	18-20	18-20	18-20	18-20	18-20	18-20
PERFORMANCE										
Dimensional Stability	EN ISO 23999	%	≤%0.4	≤%0.4	≤%0.4	≤%0.4	≤%0.4	≤%0.4	≤%0.4	≤%0.4
Curling	EN ISO 23999	mm	Max: 8	Max: 8	Max: 8	Max: 8	Max: 8	Max: 8	Max: 8	Max: 8
Tensile Strength Crosswise	EN ISO 527	N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²
Tensile strength Lengthwise	EN ISO 527	N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²	Min: 3 N/mm ²
Flexibility	EN ISO 24344		No Crack	No Crack	No Crack	No Crack	No Crack	No Crack	No Crack	No Crack

Standard products are produced with recycled PVC. Chemical structure, ingredients and chemical behaviours can not be warranted. It is optional to use only virgin raw material upon your request in case you like to have a declaration for chemical ingredients and chemical behaviors. Please kindly contact your supplier for further information.

* Sipariş geçmeden önce, lütfen güncel TDS verilerini talep edin.

* Before placing an order, please request up-to-date TDS data.